

OVERVIEW

Maximix Exterior is a skimcoat and repair compound for filling fine cracks and surface defects in light weight concrete, fairfaced dense concrete, blockwork and brickwork. It may be used on both interior and exterior surfaces to give a hard, smooth water resistant finish suitable for painting or wallpapering.

PRODUCT GRADES/CODES

Grey	77111
White	77116

PROPERTIES

Maximix Exterior is both hydraulically and organically bound, guaranteeing good adhesion to the substrate. Due to its composition and the use of precisely graded fillers, a smooth, high quality surface is obtained on walls and ceilings.

AREA OF USE

For filling or repairing fine cracks and surface defects in concrete, blockwork and brickwork, in order to produce a surface of the highest quality for final decoration.

PREPARATION OF SURFACE

Remove all oil, grease, dirt, foreign substance and loose particles. Absorbent, porous surfaces should be moistened with water prior to the application of Maximix Exterior.

On extremely absorbent, porous surfaces or under extreme climatic conditions, the standard code of practice for use of cementitious products should be followed. Priming and /or addition of one of the concentrated Terrabond bonding agents to the mixing water, ratio 1:15 bonding agent : water is recommended.

MIXING INSTRUCTIONS

Mix the Maximix Exterior with the recommended water with a high speed mixer (TERRACO SM 50 or SM 100) or with a hand agitator for 3 - 5 minutes. In normal conditions, let Maximix Exterior set for 5 minutes, restir and use.

APPLICATION AND CLEANING OF TOOLS

Maximix Exterior is applied by trowel and levelled with a steel float. Smooth finishing is achieved with a wooden or foam float when Maximix Exterior has set, moistening the float during use and brushing off loose particles with a soft brush afterwards. Maximix Exterior can also be sanded.

Clean tools and equipment with water after use.

CURING

It is advisable to keep the surface moist during the first 48 hours to ensure proper curing.

HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

PACKAGING & STORAGE

Maximix Exterior is supplied in 25kg paper bags.

Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 6 months. Use oldest material first.

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

TECHNICAL DATA

Product	Cementitious skimcoat plaster in powder form.
Binder	Hydraulic and organic binders.
Filler	Inert finely graded fillers.
Additives	Plasticizing agents, adhesion promoters and water retention agents.
Thickness of Layer	Levelling coat to a maximum of 2mm per coat.
Shrinkage	Maximum 0.13% (ATSM 157)
Consumption	Approximately 1.7kg/m ² per 1mm thickness.
Water Consumption	8.75ltr water/25kg
Packaging	25kg paper bags.
Storage	6 months in original unopened containers.

For technical enquiries please contact your nearest Terraco representative:

CHINA:

Terraco Architectural Coatings China Co., Ltd.
Tel: +86 (0)20 8759 4742
Fax: +86 (0)20 8526 8056
E-mail: sales@terraco.com.cn
Web: www.terraco.com.cn

Terraco Chemical (Shanghai) Co., Ltd.

Tel: +86 (0)21 621020 48 / 18
Fax: +86 (0)21 625205 47
Email: sales@terraco.com.cn
Web: www.terraco.com.cn

EGYPT:

Terraco Egypt Chemical Industries S.A.E.

Tel: +20 (0)22 29184 53 / 57 / 58
Fax: +20 (0)22 29184 80
E-mail: terraco@terraco.com.eg
Web: www.terraco.com.eg

JORDAN:

Jordan Swedish Polymers Industrial Corp.

Tel: +962 (0)6 553 8751
Fax: +962 (0)6 553 6560
E-mail: terraco@nol.com.jo
Web: www.terraco.jo

IRELAND:

Terraco Technical Centre, Ireland

Tel: +353 (0) 404 66555
Fax: +353 (0) 404 66654
E-mail: technical-centre@terraco.com
Web: www.terraco.com

PAKISTAN:

Terraco Pakistan Pvt. Ltd.

Tel: +92 (0)42 3529 70 56-8
Fax: +92 (0)42 3529 70 55
Email: terraco@terraco.pk
Web: www.terraco.com

ROMANIA:

Terraco Romania SRL

Tel: +40 (0)749 203 133
Fax: +40 (0)318 148 810
E-mail: ahaque@terraco.com
Web: www.terraco.com

RUSSIA:

OOO Terraco Sweden Ltd, Russia

Tel: +7 (0)495 9212 237
Fax: +7 (0)495 6273 881
E-mail: adm@terraco.ru
Web: www.terraco.ru

OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563
Fax: +7 (0)4212 410591
E-mail: terracovostok@terraccokhv.ru
Web: www.terraco.com

SOUTH KOREA:

Terraco Korea Co., Ltd

Tel: +82 (0) 2 5611 551
Fax: +82 (0)2 5671 771
E-mail: terraco@terraco.co.kr
Web: www.terraco.co.kr

THAILAND:

Terraco Industry (Thailand) Limited

Tel: +66 (0)2 946 68 56 / 58
Fax: +66 (0)2 946 68 59
E-mail: terraco@terraco.co.th
Web: www.terraco.com

TURKEY:

Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS

Tel: +90 (0)222 236 0423
Fax: +90 (0)222 236 0425
E-mail: terraco@terraco.com.tr
Web: www.terraco.com.tr

UAE:

Terraco UAE Ltd

Tel: +971 (0)4 326 2699
Fax: +971 (0)4 326 2733
E-mail: terraco@terraco.ae
Web: www.terraco.com

UK:

ADDAGRIP

Tel: +44 (0)1825 761 333
Fax: +44 (0)1825 768 566
E-mail: sales@addagrip.co.uk
Web: www.addagrip.co.uk / www.terraco.com

VIETNAM:

Terraco Vietnam Co., Ltd

Tel: +84 (0)650 3 820 100
Fax: +84 (0)650 3 820101
E-mail: terraco@terraco.com.vn
Web: www.terraco.com