

# **TERRAFIX W11**

# C1T NON-SLUMP WALL TILE ADHESIVE

# OVERVIEW PRODUCT GRADES/CODES

Terrafix W11 is a versatile wall tile adhesive with excellent non-slump characteristics. Terrafix W11 complies with the requirements as per EN12004 and passes all tests required for C1T classified adhesives. Terrafix W11 is

 Grey
 75540

 White
 75545

suitable for interior and exterior walls for use on all types of dimensionally stable masonry substrates such as sands/cement render, precast concrete, etc. Terrafix W11 is both hydraulically and organically bound, quaranteeing good adhesion of the tile to the surface.

## **PROPERTIES**

- Good adhesion
- Non-slump
- Easy workability
- Water resistant

# AREAS OF USE

General purpose non-slump ceramic and mosaic tile adhesive suitable for fixing ceramic and glass mosaic tiles to concrete swimming pools and for use on all types of dimensionally stable masonry substrates such as sand/cement render, precast concrete, etc.

# PREPARATION OF SURFACE

Ensure that the surface to be covered is clean and free of foreign matter. Absorbent and porous substrate should be wetted thoroughly with water prior to the application of Terrafix W11. Dusting surfaces should be treated with a penetrating primer.

## MIXING

Add 5.6 to 6.0 litres of water to 20kg of Terrafix W11. Add 7.0 to 7.5 litres of water to 25kg of Terrafix W11 and mix thoroughly to a thick and creamy consistency. Let it stand for 5 minutes, restir and apply.

# **APPLICATION & CLEANING OF TOOLS**

Apply Terrafix W11 in a layer approximately 3mm thick to the surface with the smooth side of a notched trowel. Pull the trowel through the applied layer with the notched edge. Push the

tiles into place so that full adhesion is obtained. Fix tiles before the adhesive has surface dried. Plan work accordingly. Prepared material must be used within 1 hour.

Clean tools and equipment with water after use.

# **SPACING OF JOINTS**

To ensure even spacing, tile spacers of the required thickness are recommended.

# GROUTING

Refer to Terragrout data sheet for details.

## **EXPANSION JOINTS**

Expansion joints, when necessary, should be incorporated in the design stage.

# **HEALTH & SAFETY**

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

# PACKAGING & STORAGE

Terrafix W11 is supplied in 20kg and 25kg craft bags.

Store containers in a clean dry area protected from high humidity, moisture, direct sunlight, extreme heat and cold. Unopened containers can be stored for 12 months. Use oldest material first.

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.



# **TERRAFIX W11**

# **C1T NON-SLUMP WALL TILE ADHESIVE**

TECHNICAL DATA	
Product	Non-slump wall tile adhesive.
Binder	Hydraulic and organic binders.
Filler	Inert finely graded fillers.
Colour	Grey/ white.
Additives	Plasticizing agents, adhesion improving substances, as well as water retaining agents.
Quality Type	Passes tests as per C1T/EN12004.
Tensile Adhesion	Standard condition: EN1348 > 0.5 N/mm <sup>2</sup> Heat aging: EN1348 > 0.5 N/mm <sup>2</sup> After water immersion: EN1348 > 0.5 N/mm <sup>2</sup> After freeze/thaw cycle: EN1348 > 0.5 N/mm <sup>2</sup>
Application Temperature	5-35°C
Consumption	Trowel No. 4: 2.0-2.5 kg/m <sup>2</sup> Trowel No. 5: 2.5-3.0 kg/m <sup>2</sup> Trowel No. 6: 4.0-6.0 kg/m <sup>2</sup>
Mixing Water %	28-30%
Adjustability Time	>30 minutes.
Pot Life	2 hours.
Open Time	>20 minutes
Ready to Grout	24 hours
Ready for Use	14 days
Packaging	20kg and 25kg craft bags.
Storage	12 months in original unopened containers.

For technical enquiries please contact your nearest Terraco representative:

## CHINA:

# Terraco Architectural Coatings China Co., Ltd.

Tel: +86 (0)20 8759 4742 Fax: +86 (0)20 8526 8056 E-mail: sales@terraco.com.cn Web: www.terraco.com.cn

#### Terraco Chemical (Shanghai) Co., Ltd.

Tel: +86 (0)21 621020 48 / 18 Fax: +86 (0)21 625205 47 Email: sales@terraco.com.cn Web: www.terraco.com.cn

## EGYPT:

## Terraco Egypt Chemical Industries S.A.E.

Tel: +20 (0)22 29184 53 / 57 / 58 Fax: +20 (0)22 29184 80 E-mail: terraco@terraco.com.eg Web: www.terraco.com.eg

#### JORDAN:

# Jordan Swedish Polymers Industrial Corp.

Tel: +962 (0)6 553 8751 Fax: +962 (0)6 553 6560 E-mail: terraco@nol.com.jo Web: www.terraco.jo

# IRELAND:

#### Terraco Technical Centre, Ireland

Tel: +353 (0) 404 66555 Fax: +353 (0) 404 66654 E-mail: technical-centre@terraco.com Web: www.terraco.com

## PAKISTAN:

# Terraco Pakistan Pvt. Ltd.

Tel: +92 (0)42 3529 70 56-8 Fax: +92 (0)42 3529 70 55 Email: terraco@terraco.pk Web: www.terraco.com

#### RUSSIA:

## OOO Terraco Sweden Ltd, Russia

Tel: +7 (0)495 9212 237 Fax: +7 (0)495 6273 881 E-mail: adm@terraco.ru Web: www.terraco.ru

### OOO Terraco Vostok Ltd

Tel: +7 (0)4212 410563 Fax: +7 (0)4212 410591 E-mail: terracovostok@terracokhv.ru Web: www.terraco.com

#### **SOUTH KOREA:**

# Terraco Korea Co., Ltd

Tel: +82 (0) 2 5611 551 Fax: +82 (0)2 5671 771 E-mail: terraco@terraco.co.kr Web: www.terraco.co.kr

#### THAILAND:

#### Terraco Industry (Thailand) Limited

Tel: +66 (0)2 946 68 56 / 58 Fax: +66 (0)2 946 68 59 E-mail: terraco@terraco.co.th Web: www.terraco.com

#### TIIRKFY:

# Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS

Tel: +90 (0)222 236 0423 Fax: +90 (0)222 236 0425 E-mail: terraco@terraco.com.tr Web: www.terraco.com.tr

# UAE:

## Terraco UAE Ltd

Tel: +971 (0)4 326 2699 Fax: +971 (0)4 326 2733 E-mail: terraco@terraco.ae Web: www.terraco.com

# UK:

#### **ADDAGRIP**

Tel: +44 (0)1825 761 333 Fax: +44 (0)1825 768 566 E-mail: sales@addagrip.co.uk

Web: www.addagrip.co.uk / www,terraco.com

### VIETNAM:

#### Terraco Vietnam Co., Ltd

Tel: +84 (0)650 3 820 100 Fax: +84 (0)650 3 820101 E-mail: terraco@terraco.com.vn Web: www.terraco.com